

Specification Sheet

Product Description: Silicon Dioxide

Parameter	Method	Limits	Unit
pH (5% Solution)	LAB-1543	6.0 – 7.3	pH Units
Loss on Drying (2hrs @ 105°C)	LAB-1530	≤8.0	%
Loss on Ignition @ 1000°C	LAB-1530	≤12.5	%
Soluble Salts (as Na ₂ SO ₄)	LAB-1541	≤4.0	%
Median Particle Size D ₅₀	LAB-1536	15-22	µm

AsiAmerica Group, Inc.
85 Chestnut Ridge Road, Suite 218
Montvale, NJ 07645

Tel: (201) 497-5993
Fax: (201) 497-5994

